

## TECHNICAL DATA SHEET FOR PROCURE PC07

### PRODUCT DESCRIPTION

PC07 is a medium to high viscosity Cyanoacrylate adhesive suitable for filling, bonding large bond gaps. PC07 is a one-component, solvent-free system and does not require the use of a catalyst, heat or clamps. When a thin layer of PC07 applied between two surfaces comes into contact with atmospheric moisture, a rapid polymerization occurs producing the ultimate bond.

Liquid State		Cured State	
Base	Ethyl Cyanoacrylate	Color	Clear
Color	Clear	Specific Gravity(20°C)	1.1~1.3
Specific Gravity (0°C)	1.053~1.060	Working Temperature (°C)	-55°C - 80°C
Refractive Index (n <sub>D</sub> <sup>20</sup> )	1.439	Refractive Index(n <sub>D</sub> <sup>20</sup> )	1.490
Flash Point (°C)	>80°C	Dielectric Constant (at 10MHz)	3.5
Shelf Life	12 Months	Dielectric Loss(at 10MHz)	0.067
Boiling Point(°C)	65/6mm Hg	Soluble in Acetone, Dimethyl formamide, nitromethane, Dimethyl sulfoxide	
Viscosity(cP).....		<b>PC07</b> .....	700-1000

### DIRECTIONS FOR USE

1. Make sure the surfaces to be bonded are clean and dry (preferable to solvent-wipe plastics glass, and rubber, and to acid-treat metals).
2. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film after compression.
3. Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute. (Maximum strength is achieved in 24 to 48 hours).
4. Wipe off excess adhesive from the top of the container and recap PC07 if left uncapped, may deteriorate by contamination from moisture in the air.
5. Because PC07 polymerises on contact with moisture surfaces, sometimes whitening will occur on the surface of the container or the bonded materials. Should this happen, wipe surfaces well with de-bonder.

## TECHNICAL DATA SHEET FOR PROCURE PC07

### BOND STRENGTH

	KG/CM <sup>2</sup>		KG/CM <sup>2</sup>
Rigid PVC to Rigid PVC	50-70	SBR to SBR	5-10
ABS to ABS	50-70	Steel to Steel	200-220
Polycarbonate to Polycarbonate	70-120	Stainless steel to Stainless steel	200-220
Polystyrene to Polystyrene	40-45	Aluminum to Aluminum	170-190
Natural rubber to Natural rubber	5-10	Copper to Copper	150-170
*Neoprene to Neoprene	5-10	Steel to Rigid PVC	40-60
NBR to NBR.....	5-10	Stainless steel to Neoprene	5-10
ABS to SBR.....	5-10		

### CURE SPEED

PC07	Seconds		Seconds
ABS to ABS	15-20	NBR to NBR	3-5
Wood to Wood	>60	Stainless steel to Stainless steel	23-30
ABS to Stainless steel	12-15	ABS to NBR	3-5
NBR to Stainless steel	10-12	Wood to ABS	40-50

### PRECAUTIONS

1. Use with proper ventilation. Avoid contact with skin and eyes.
2. If contact with skin occurs, rinse with warm water or dissolve gradually with appropriate debonder. Do not try to remove forcibly.
3. If adhesive gets into eye, keep eye open and rinse thoroughly. Seek medical attention immediately.
4. Keep well out of reach of children.
5. Keep adhesive in a cool, dry place 20-25°C. For long term storage, refrigeration (5°C) is recommended.

### DISCLAIMER

The data contained herein are furnished for informational purposes only and are believed to be reliable. However, Cyanotec Ltd does not assume responsibility for any results obtained by persons over whose methods Cyanotec Ltd has no control. It is the user's responsibility to determine the suitability of Cyanotec products or any production methods mentioned herein for a particular purpose, and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use of any Cyanotec Ltd's products. Cyanotec Ltd specifically disclaims all warranties express or implied, including warranties of salability and suitability for a particular purpose arising from sale or use of Cyanotec Ltd's products. Cyanotec Ltd further disclaims any liability for consequential or incremental damages of any kind including lost profits.

#### CYANOTEC LTD

Bay 2, Building 62, Third Avenue, Pensnett Trading Estate, Kingswinford DY6 7XT  
TEL 0845 618 3120 FAX 0845 618 3121 EMAIL sales@cyanotec.com

PC 07  
V1.3  
JUN 16