

QT269

General Purpose PVC Tape



Product Description

QT269 is a flexible tape used as general purpose product, suitable for many applications as economic floor marking tape, for repairing, jointing PE foils, barrier tape to prevent electrolytic reaction between dissimilar metals, sealing boxes and drums.

Features

- Highly Flexible

Main Applications

- Economy Floor marking
- Repairing and Jointing PE Foils
- Used as barrier to prevent Electronic reaction between dissimilar metals
- Sealing boxes and drums

Technical Data

	Units	Std. Values
Total Thickness	µm	130
Backing Thickness	µm	115
MD tensile strength	N/cm	22
MD elongation at break	%	180
Peel Adhesion	N/cm	1.6
Service Temperature	°C	-10, +80

Backing material

PVC

Type of adhesive

Natural Rubber (Solvent Borne)

Available colour



Technical Information and Product Use

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. Qualitape (UK) Ltd reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

Storage and Shelf Life

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of manufacture. Qualitape (UK) Ltd does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.