

NOVOPROOF® FA EPDM CORNERS



INSIDE CORNER



OUTSIDE CORNER

Product

Preformed inside and outside corners made of NOVOPROOF® EPDM (Ethylene Propylene Diene Monomer).

Application examples

- For a perfect finishing and sealing of corners around windows, in cavity walls
- For curtain facades
- For steel facades
- For outside facade insulation

Colour

Black

Thickness

0.75mm, 1mm, 1.3mm, 1.50 mm

Dimensions

- Inside corners : 10 x 10 x 10cm
- Outside corners : 10 x 10 x 10cm & 20 x 20 x 20cm
- Other dimensions on request

Properties

- ✓ Excellent resistance to weather conditions, UV-rays and ageing
- ✓ Excellent waterproofing on the long term
- ✓ Elastic
- ✓ Lightweight and recyclable
- ✓ Good thermal insulation
- ✓ Solvent-free



Building bonding paste NOVOPROOF® FA

A one-component special adhesive and sealant based on synthetic rubber, which cures to a durable elastic rubber. Colour: black. Especially developed for bonding and sealing the NOVOPROOF® FA EPDM on the most common building materials such as aluminum (untreated, anodized, powder-coated), mineral surfaces (concrete, stone, brick, plaster), steel (galvanized, powder-coated), wood (test before application), overlaps between EPDM panels.
Aluminium Sausages of 600 ml (12).



NOVOPROOF® Kleber TA

Contact adhesive based on synthetic rubber used for bonding the membrane on various substrates (wood, aluminum and stone).



NOVOPROOF® Primer

Adhesion promoter for the use of the contact adhesive Kleber TA or the building bonding paste NOVOPROOF FA on porous, moist surfaces or when using them at temperatures between + 3 °C and - 10°C.



Technical properties

Property	Value + unit
Density	1,830 Kg/m ²
Hardness shore A	65° +/- 5
Temperature resistance EPDM	-30°C to +116°C
Elongation at break (EN 12311-1)	≥ 500 %
Tensile strength (EN 12311-1)	≥ 460 N/50 mm
Tear resistance (EN 12310-1)	≥ 130 N
Reaction to fire (EN ISO 11925-2/EN 13501-1)	E
Resistance to air passage	≤ 0,1 m ³ /(m ² /h/50 Pa)
Resistance to vapour diffusion (μ)	60.000 +/- 18.000
Certificates	ATG 12/2891

NOVOPROOF® Cleaner

Used for cleaning the EPDM FA (if not clean enough) before gluing it with the building bonding paste FA or with the contact Kleber TA.



Note

The details and information given in this literature are based on best current knowledge. They are intended to serve as general information only and it is advised that the user conducts their own tests for their specific set of conditions to determine the suitability of the product for its proposed use. No warranty or liability is given or implied regarding any part of these instructions or details, or the completeness of the information. We reserve the right to modify, or change, the specifications and information without advance notification. All goods are supplied subject to our standard conditions of sales, copies of which are available upon request.

Technical data of supplier: 05 2014

The producer reserves the right to make changes. 2015 10 11